

Celvol® E 4/88S Polyvinyl Alcohol

DESCRIPTION

CELVOL E 4/88S is a low viscosity partially hydrolysed polyvinyl alcohol which finds applications principally in the Building industry.

COMMERCIAL SPECIFICATIONS

IT 06-04-101 P

Test	Specification	Method	Internal Reference	International Reference
Viscosity ^(a) (cps)	4.0 - 5.0	Brookfield	IT 06-06-225 P	ISO 2555
Degree of Hydrolysis Mol %	87.0 - 89.0	Titration	IT 06-06-224 P	
Ash ^(b) Wt %	0.5 Max.	Conductimetry	IT 06-06-220 P	
Volatile Wt %	5.0 Max.	Drying	IT 06-06-221 P	
pH ^(c)	5.0 - 7.0	Potentiometry	IT 06-06-226 P	ISO 1148
Particle size	0.1 % Max upper 200 µm	Granulometry	IT 06-06-227 P	

(a) Of a 4% aqueous solution at 20°C (b) Expressed as Sodium Oxide (c) Of a 4% aqueous solution

GENERAL PROPERTIES

Appearance	Off white granular solid
Refractive Index $n_D^{20^\circ C}$	1.52 - 1.55
Specific gravity	1.27 - 1.31
Specific heat (J/g K)	1.65 - 1.67
Thermal conductivity (W/m C)	~2
Mean coefficient of thermal expansion at 0-45°C (x 10 ⁻⁵ / °C)	7-10
Glass transition temperature (°C)	58
Melting point (°C)	180
Light stability	Excellent
Electrical resistivity (Ω cm x 10 ⁷)	3.1 - 3.8

APPLICATIONS

Building: Cement for mortars, building adhesives and gypsum boards.

PACKAGING

CELVOL E 4/88S can be made available in the following packaging:

- 25 Kg Antistatic Polyethylene bags palletised on CPI pallets 1.00 TM (shrink wrapped or stretch wrapped) 4 way entry pallets.
- 500 Kg Polypropylene Rafia Big Bag palletised on 90 x 90 cm (stretch wrapped) 4 way entry pallets.
- Other packaging may be available on request.



STORAGE

CELVOL E 4/88S Polyvinyl alcohol is stable over a long period of storage under dry conditions.

TRANSPORT

Not regulated.

HEALTH , SAFETY , ENVIRONMENT

Please refer to the CELVOL Material Safety Data Sheet for the product.

OTHER INFORMATION

- Customs Tarif No: 3905.3000.
- Polyvinyl alcohol is registered in the following inventories: AICS (Australia), CEPA DSL (Canada), TSCA (United States), MITI (Japan), AUSTRIA, CHINA, PHILIPPINES and SOUTH KOREA.
- CAS NUMBER: 25213-24-5

FOOD CONTACT STATUS

CELVOL E 4/88S conforms to various FDA and BfR regulations for use in food contact applications. The user should check the regulation corresponding to the proposed application, in order to verify that the CELVOL grade to be used is within the specified limitations. For more details the user is invited to contact our customer service department.

North America

Sekisui Specialty Chemicals America, LLC
1603 West LBJ Freeway, Suite 200
Dallas, TX 75234 USA
Tel: +1-972-277-2900
Fax: +1-972-277-2907

Europe

Sekisui Specialty Chemicals Europe, S.L.
Ctra. N-340, Km 1157
Apartado 1388
43080 Tarragona, Spain
Tel: + 34-977-548-899
Fax: + 34-977-544-982

www.sekisui-sc.com

To the best of our knowledge, the information contained herein is accurate. However Sekisui assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of suitability of any material and whether there is any infringement of patents is the sole responsibility of the user. All chemicals may present unknown health hazards and should be used with caution. Although certain hazards may be described in this publication, we cannot guarantee that these are the only hazards that exist. Users of any chemical should satisfy themselves by independent investigation of current scientific and medical knowledge that the material can be used safely. In addition, no certification or claim is made as to the status, under any law or regulation, including but not limited to the Toxic Substances Control Act of either the chemicals discussed above or any subsequent polymerization or reaction products that result from a formulation containing them.