



Selvol™ Polyvinyl Alcohol 350

SALES SPECIFICATION

Specifications		Limits
Hydrolysis, mole%		98.40 +/- 0.40
4% Solution Viscosity, cP ¹		67.00 +/-5.00
Total Volatiles, wt% ²	Max.	5.00
Total Organic Volatiles, wt%	Max.	1.00
Methanol, wt%	Max.	0.90
Ash - ISE, wt% ³	Max.	1.20
4% Solution pH ⁴		6.00 +/- 1.00

¹ 4% aqueous solution, 20°C

² Total volatiles including water

³ As % Na₂O, corrected volatiles

⁴ 4% aqueous solution

North America

Sekisui Specialty Chemicals America, LLC
1501 West LBJ Freeway, Suite 530
Dallas, TX 75234 USA
Tel: +1-972-277-2900
Fax: +1-972-277-2907

Europe

Sekisui Specialty Chemicals Europe, S.L.
Ctra. N-340, Km 1157
Apartado de Correos 1388
43080 Tarragona, Spain
Tel: + 34-977-549-899
Fax: + 34-977-544-982

www.Sekisui-sc.com
www.Selvol.com

SSC350
Revision 3: 7/2012

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application or purpose. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.