



## Selvol™ Polyvinyl Alcohol 425

### SALES SPECIFICATION

Specifications		Limits
Hydrolysis, mole%		96.00 +/- 0.50
4% Solution Viscosity, cP <sup>1</sup>		29.00 +/- 2.00
Total Volatiles, wt% <sup>2</sup>	Max.	5.00
Total Organic Volatiles, wt%	Max.	1.00
Methanol, wt%	Max.	0.90
Ash - ISE, wt% <sup>3</sup>	Max.	0.90
4% Solution pH <sup>4</sup>		5.50 +/- 1.00

<sup>1</sup> 4% aqueous solution, 20°C

<sup>2</sup> Total volatiles including water

<sup>3</sup> As % Na<sub>2</sub>O, corrected volatiles

<sup>4</sup> 4% aqueous solution

#### North America

Sekisui Specialty Chemicals America, LLC  
1501 West LBJ Freeway, Suite 530  
Dallas, TX 75234 USA  
Tel: +1-972-277-2900  
Fax: +1-972-277-2907

#### Europe

Sekisui Specialty Chemicals Europe, S.L.  
Ctra. N-340, Km 1157  
Apartado de Correos 1388  
43080 Tarragona, Spain  
Tel: + 34-977-549-899  
Fax: + 34-977-544-982

[www.Sekisui-sc.com](http://www.Sekisui-sc.com)  
[www.Selvol.com](http://www.Selvol.com)

SSC425  
Revision 3: 7/2012

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application or purpose. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.