

# Selvol™ Ultalux® AD

## ESPECIFICACIONES COMERCIALES

Especificaciones		Límites
Viscosidad (Solución 8%), cP		30.0 +/- 15.0
Volátiles totales, %Peso <sup>1</sup>	Max.	5.0
Compuestos Orgánicos Volátiles, %Peso		< 3.0
Cenizas - ISE, %Peso <sup>2</sup>	Max.	3.0
pH (Solución 4%) <sup>3</sup>		11.5 +/- 0.5

<sup>1</sup> Volátiles totales incluida el agua

<sup>2</sup> Expresado como Na<sub>2</sub>O

<sup>3</sup> Solución acuosa al 4%

Otras Propiedades	Valor
Contenido en Metales Pesados, mg/kg <sup>4</sup>	≤10 mg/kg
Viscosidad (Solución 15%), cP	500 ± 50

<sup>4</sup>Verificado semestralmente por un laboratorio independiente usando un método USP/NF para Metales Pesados.

**Nombre INCI:** Vinyl Amine/Vinyl Alcohol Copolymer

### North America

Sekisui Specialty Chemicals America, LLC  
 1501 West LBJ Freeway, Suite 530  
 Dallas, TX 75234 USA  
 Tel: +1-972-277-2900  
 Fax: +1-972-277-2907

### Europe

Sekisui Specialty Chemicals Europe, S.L.  
 Ctra. N-340, Km 1157  
 Apartado de Correos 1388  
 43080 Tarragona, Spain  
 Tel: + 34-977-549-899  
 Fax: + 34-977-544-982

[www.Sekisui-sc.com](http://www.Sekisui-sc.com)

SSCUltalux AD  
 11/2013\_r01

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application or purpose. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.